


WEATHER XL[™] GLOSS & MATTE COLORS -







SHADOW DEEP GRAY Signature Matte Finish




BURNISHED SLATE Signature Matte Finish



ANTIQUE BROWN



HARVEST CEDAR



SILVER SPRINGS

13 9/16" (345 mm)

- Superior resistance to chalking, fading and scratching.
- Exceptional color & gloss retention.
- Outstanding color consistency.

TRUEMETALSUPPLY.COM

(865) 224-3055

• Superior weatherability.

50" (1270 mm)

Actual colors may vary slightly. Final color selection should be made from actual color chips.



1745 LOUISVILLE DRIVE KNOXVILLE, TN 37921

EBONY



experience true service

Technical Data

Specular Gloss at 60° ASTM D523 ²	25 to 35 for Matte Finish <1045
Pencil Hardness ASTM D3363	F to 2H
T-Bend ASTM D4145 ⁵	2T to 4T ³ with no loss of adhesion
Cross Hatch Adhesion ASTM D3359	No loss of adhesion
Reverse Impact ASTM D2794 ⁵	Galvalume® or HDG: 3x³ metal thickness inch- pounds, no loss of adhesion Aluminum: 1.5x metal thickness inch-pounds, no loss of adhesion
Humidity Resistance 100% RH 1,000 Hours ASTM D2247 100% RH 2,000 Hours ASTM D2247	Galvalume® or HDG: No field blisters Aluminum: No field blisters
Salt Spray Resistance 1,000 Hours ASTM B117 2,000 Hours ASTM B117	Galvalume® or HDG: Creep from scribe ≤ 1/8 inch (3mm), none or few #8 blisters Aluminum: Creep from scribe ≤ 1/8 inch (3mm), few #8 blisters
South Florida Exposure ASTM D2244 ASTM D659 ¹	Color: No more than 5∆E Hunter units at 90° vertical angle & 7∆E nonvertical at 30 yrs Chalk: Rating no less than 8 at 90° angle and 6 at non vertical angle at 30 yrs Film Integrity: 40 years, no cracking, flaking and peeling
Water Immersion 100° F 168 Hours ASTM D870	No field blisters with minimal color change
Abrasion Resistance: ASTM D968	Total sand = 35 + 5 liters

Abrasion Resistance: ASTM D968


Total sand = 35 ± 5 liters

Application Characteristics

Application Method	Reverse roll coat
Substrate ¹	Aluminum, HDG or Galvalume®
Dry Film Thickness ASTM D4138	Top coat: 0.7 to 0.8 mils Primer: 0.2 to 0.3 mils Total system: 0.9 to 1.1 mils
Viscosity ASTM D4212 (No. 4 Zahn cup)	25 to 45 seconds
Weight per Gallon ASTM D1475	9.0 to 12.0 pounds per gallon
VOC (Theoretical) ASTM D3960	3.0 to 4.0 pounds per gallon ⁴
Peak Metal Temperature	420° to 450° F
Contains Lubricant	Yes
MEK Double Rubs ASTM D5402	150 Plus

Seeing is believing.

Check out our website to find the right metal roof for your home!



TRUEMETALSUPPLY.COM (865) 224-3055



1745 LOUISVILLE DRIVE KNOXVILLE, TN 37921